

## FOROLEN<sup>®</sup> PP(2050MN)

MATERIAL NAME: PP

COLOR: NATURAL

CODE: 2050MN

MATERIAL DESCRIPTION: Forolen<sup>®</sup> PP 2050MN is a 20% mineral filled, prime, natural homo Polypropylene for injection molding.

No.	PROPERTIES		METHOD	UNIT	VALUE
<b>PHYSICAL PROPERTIES</b>					
1	ASH CONTENT		ISO 3451	%	20
2	RELATIVE DENSITY		ISO 1183	g/cm <sup>3</sup>	1.06
3	VISCOSITY NUMBER		ISO 307	Cm <sup>3</sup> /gr	-
4	MOISTURE CONTENT		ISO 62	%	0.23
<b>MECHANICAL PROPERTIES</b>					
5	TENSIL STRENGTH AT BREAK (5mm/min)		ASTM/D638	MPa	26
6	ELONGATION AT BREAK (5mm/min)		ASTM/D638	%	60
7	TENSIL MODULUS (5mm/min)		ASTM/D638	MPa	2100
8	NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m <sup>2</sup>	5.5
9	UN NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m <sup>2</sup>	49
<b>THERMAL PROPERTIES</b>					
10	HARDNESS		ISO 868	Shore D	65
11	MFI		ASTM/D1238	g/10min	31
12	VICAT(50° C/h)	10N	ASTM/D1238	° C	129
		50N			82
<b>FLAMMABILITY</b>					
13	HDT (120° C/h)	264psi	ASTM/D648	° C	65
		66psi			110
14	Flammability	Class	UL94	-	-
<b>INJECTION PROCESS PARAMETERS</b>					
<i>Loading</i>		<i>Injection</i>		<i>Degassing</i>	
<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Temperature</i>	<i>Time</i>
60	80	60	80	50 °C	0.5h
<i>Mold Releasing</i>		<i>Zone</i>			
<i>Good</i>		5	4	3	2
		- °C	165 °C	170 °C	175 °C
					1
					180 °C