

KIMIALON[®] 6.6(N112R)

MATERIAL NAME: PA6.6

COLOR: NATURAL

CODE: N112R

MATERIAL DESCRIPTION: Kimialon[®] N112R is a high impact modified, un-reinforced, lubricated, natural color regenerated Polyamide 6.6 resin for injection molding.

No.	PROPERTIES		METHOD	UNIT	VALUE
PHYSICAL PROPERTIES					
1	ASH CONTENT		ISO 3451	%	0.00
2	RELATIVE DENSITY		ISO 1183	g/cm ³	1.1
3	VISCOSITY NUMBER		ISO 307	Cm ³ /gr	---
4	MOISTURE CONTENT		ISO 62	%	0.27
MECHANICAL PROPERTIES					
5	TENSIL STRENGTH AT BREAK (5mm/min)		ASTM/D638	MPa	50
6	ELONGATION AT BREAK (5mm/min)		ASTM/D638	%	86.0
7	TENSIL MODULUS (5mm/min)		ASTM/D638	MPa	2500
8	NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	48
9	UN NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	N.B
THERMAL PROPERTIES					
10	HARDNESS		ISO 868	Shore D	69
11	MFI		ASTM/D1238	g/10min	-
12	VICAT(50° C/h)	10N	ASTM/D1238	° C	198
		50N			89
FLAMMABILITY					
13	HDT (120° C/h)	264psi	ASTM/D648	° C	61
		66psi			182
14	Flammability	Class	UL94	-	-
INJECTION PROCESS PARAMETERS					
<i>Loading</i>		<i>Injection</i>		<i>Degassing</i>	
<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Temperature</i>	<i>Time</i>
60	80	70	90	50 °C	0.5h
<i>Mold Releasing</i>		<i>Zone</i>			
<i>Good</i>		5	4	3	2
		- °C	260 °C	265 °C	270 °C