

FOROLEN[®] PP(3040MN)

MATERIAL NAME: PP

COLOR: NATURAL

CODE: 3040MN

MATERIAL DESCRIPTION: Forolen[®] PP3040MN is a 30% mineral filled, prime, natural Polypropylene for injection molding.

No.	PROPERTIES		METHOD	UNIT	VALUE
PHYSICAL PROPERTIES					
1	ASH CONTENT		ISO 3451	%	30
2	RELATIVE DENSITY		ISO 1183	g/cm ³	1.12
3	VISCOSITY NUMBER		ISO 307	Cm ³ /gr	-
4	MOISTURE CONTENT		ISO 62	%	0.22
MECHANICAL PROPERTIES					
5	TENSIL STRENGTH AT BREAK (5mm/min)		ASTM/D638	MPa	18
6	ELONGATION AT BREAK (5mm/min)		ASTM/D638	%	200
7	TENSIL MODULUS (5mm/min)		ASTM/D638	MPa	1500
8	NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	13
9	UN NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	N.B
THERMAL PROPERTIES					
10	HARDNESS		ISO 868	Shore D	61
11	MFI		ASTM/D1238	g/10min	19
12	VICAT(50° C/h)	10N	ASTM/D1238	° C	122
		50N			85
FLAMMABILITY					
13	HDT (120° C/h)	264psi	ASTM/D648	° C	64
		66psi			112
14	Flammability	Class	UL94	-	-
INJECTION PROCESS PARAMETERS					
<i>Loading</i>		<i>Injection</i>		<i>Degassing</i>	
<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Temperature</i>	<i>Time</i>
60	80	80	100	50 °C	0.5h
<i>Mold Releasing</i>			<i>Zone</i>		
<i>Good</i>			5	4	3
			- °C	165 °C	170 °C
				2	1
				175 °C	180 °C