

KIMIALON[®] PA6 (N220GV0)

MATERIAL NAME: PA6 **COLOR:** NATURAL **CODE:** N220GV0

MATERIAL DESCRIPTION: Kimialon[®] PA6 (N220GV0) is a flame retardant, 20% glass fiber reinforced, natural Polyamide 6 resin for injection molding.

No.	PROPERTIES		METHOD	UNIT	VALUE
PHYSICAL PROPERTIES					
1	ASH CONTENT		ISO 3451	%	28.8
2	RELATIVE DENSITY		ISO 1183	g/cm ³	1.44
3	VISCOSITY NUMBER		ISO 307	Cm ³ /gr	-
4	MOISTURE CONTENT		ISO 62	%	0.26
MECHANICAL PROPERTIES					
5	TENSIL STRENGTH AT BREAK (5mm/min)		ASTM/D638	MPa	125
6	ELONGATION AT BREAK (5mm/min)		ASTM/D638	%	8.5
7	TENSIL MODULUS (5mm/min)		ASTM/D638	MPa	7000
8	NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	8.0
9	UN NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	40
THERMAL PROPERTIES					
10	HARDNESS		ISO 868	Shore D	75
11	MFI		ASTM/D1238	g/10min	-
12	VICAT(50° C/h)	10N	ASTM/D1238	° C	220
		50N			210
FLAMMABILITY					
13	HDT (120° C/h)	264psi	ASTM/D648	° C	206
		66psi			219
14	Flammability	Class	UL94	-	V0
INJECTION PROCESS PARAMETERS					
<i>Loading</i>		<i>Injection</i>		<i>Degassing</i>	
<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Temperature</i>	<i>Time</i>
60	80	80	100	80 °C	1h
<i>Mold Releasing</i>		<i>Zone</i>			
<i>Good</i>		5	4	3	2
		- °C	210 °C	215 °C	220 °C